

Introduction


TT 1000 granulate is an inorganic, flowable, and pourable microporous material with excellent thermal properties. It features very low thermal conductivity and maintains a very low density even after compaction. It is suitable for filling complex shapes or geometries with limited space structures and where shaped and rigid insulation cannot be applied.



Technical Data

Thermal Conductivity

20 °C / 68 °F	0.030 W/m K
200 °C / 392 °F	0.034 W/m K
400 °C / 752 °F	0.039 W/m K
600 °C / 1112 °F	0.046 W/m K
800 °C / 1472 °F	0.054 W/m K



Other Technical Parameters

classification temperature	1000 °C / 1832 °F
bulk density	160 kg/m ³
tap density	185 kg/m ³
density tolerance	± 30 kg/m ³

Package

standard package	230 kg/pallet, other package can be customized
------------------	--

Benefits

Very low thermal conductivity provides reduction of energy consumption;

Low in weight allows a compact and light system structure;

Cost efficient insulations for complex geometries;

Inorganic and non-combustible;

Environmental friendly.

Typical Applications

Unicorn granulate can be used in any application requiring a pourable insulation where space is limited and shape is complex:

Industrial chimney walls;

Fuel cells;

Complex kiln cars;

High temperature boxes and any other complex cavities.

Technical Limitation

Water and other liquids will irreversibly destroy and microporous structure and as a result the insulation performance of the material.



unicorn-insulations.com
info@unicorn-insulations.com

ISO9001:2015
CERTIFIED



Disclaimer: The information contained in this brochure and datasheets is intended to assist with the usage of unicorn insulations products. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the result shown in this brochure will be achieved by a user for a particular purpose. The user is responsible for determining the suitability of unicorn insulations products for each application. The user is obliged to check the intended usage of the material in terms of infringement on any intellectual property of a third party.